REQUIREMENTS FOR CORRUGATED STEEL PIPE THICKNESS AND PROTECTION AT ABRASIVE SITES

| pН | ≤4.0 | 4.5 | 5.0 | 5.5 | 6.0 | 6.5 | ≥7.0 | Steel Conduit Type |
|---|----------|----------|----------|-------|-------|-------|-------|---|
| Thickness (in.) required for 50 year | X | X | X | 0.168 | 0.168 | 0.138 | 0.109 | Zinc Coated Corrugated Steel Pipe w/Paved Invert Zinc Coated Corrugated Steel Pipe-Arch w/Paved Invert Fully Bituminous Coated and Lined Corrugated Steel Pipe Fully Bituminous Coated and Lined Corrugated Steel Pipe-Arch |
| Design Service | \times | \times | 0.138 | 0.109 | 0.109 | 0.079 | 0.064 | Aluminum Coated Type 2 Corrugated Steel Pipe w/Paved Invert Aluminum Coated Type 2 Corrugated Steel Pipe-Arch w/Paved Invert |
| Life | 0.109 | 0.109 | 0.079 | 0.064 | 0.064 | 0.064 | 0.064 | Polymer Precoated Galvanized Corrugated Steel Pipe w/Paved Invert Polymer Precoated Galvanized Corrugated Steel Pipe-Arch w/Paved Invert Fiber Bonded Bituminous Coated Corrugated Steel Pipe w/Paved Invert Fiber Bonded Bituminous Coated Corrugated Steel Pipe-Arch w/Paved Invert |
| | X | \times | \times | 0.170 | 0.111 | 0.111 | 0.111 | Structural Plate Steel Pipe w/Concrete Field Paving Structural Plate Steel Pipe-Arch w/Concrete Field Paving |

| pН | ≤4.0 | 4.5 | 5.0 | 5.5 | 6.0 | 6.5 | ≥7.0 | Steel Conduit Type |
|---|-------|----------|----------|-------|-------|-------|-------|---|
| Thickness (in.) required for 75 year | X | X | X | X | X | 0.168 | 0.138 | Zinc Coated Corrugated Steel Pipe w/Paved Invert Zinc Coated Corrugated Steel Pipe-Arch w/Paved Invert Fully Bituminous Coated and Lined Corrugated Steel Pipe Fully Bituminous Coated and Lined Corrugated Steel Pipe-Arch |
| Design | X | \times | \times | 0.168 | 0.168 | 0.138 | 0.109 | Aluminum Coated Type 2 Corrugated Steel Pipe w/Paved Invert Aluminum Coated Type 2 Corrugated Steel Pipe-Arch w/Paved Invert |
| Service Life | 0.168 | 0.168 | 0.168 | 0.138 | 0.138 | 0.109 | 0.109 | Polymer Precoated Galvanized Corrugated Steel Pipe w/Paved Invert Polymer Precoated Galvanized Corrugated Steel Pipe-Arch w/Paved Invert Fiber Bonded Bituminous Coated Corrugated Steel Pipe w/Paved Invert Fiber Bonded Bituminous Coated Corrugated Steel Pipe-Arch w/Paved Invert |
| | X | \times | \times | 0.218 | 0.111 | 0.111 | 0.111 | Structural Plate Steel Pipe w/Concrete Field Paving Structural Plate Steel Pipe-Arch w/Concrete Field Paving |

Refer to Standard Drawing E 715-PSLC-03 for General Notes.

